

# Vinitex WS 1.2

## DESCRIPTION

VINITEX WS 1.2 is a non-reinforced flexible PVC membrane which is 1.2 mm thick.

## APPLICATIONS

Water-proofing reservoirs, ponds or channels, suitable for outdoor use.

## PROPERTIES

- Membrane made exclusively from virgin resins.
- Very long-lasting.
- Highly puncture resistant.
- Excellent stability under UV radiation.
- Excellent adaptability to the land
- Excellent mechanical properties
- Easily welded using hot air, even several years after installation.
- Resistant to micro-organisms.

## INSTALLATION

- VINITEX WS 1.2 waterproofing systems must be installed by experienced and qualified personnel.
- Surfaces must be clean and dry and free from sharp obtrusions. The membrane can be used on bitumen, asphalt, oil and tar surfaces and polyurethane and polystyrene isolation by using a suitable geotextile as a separating layer.
- Membrane joints should be made using a hot air welder and should be checked by running a flat headed punch along the whole of the seam.
- Before starting welding adjust the parameters for speed and temperature according to the ambient conditions and the surfaces of the membrane.

## PACKAGING AND STORAGE

Colours	Grey
Dimensions	2,05 x 20 m (41 m <sup>2</sup> / roll)
Rolls / pallet	18
Storage	Horizontally and in parallel (never crossed)

Supplied in rolls on cardboard tubing.  
Store in the original packaging in a dry and cool place.

TEXSA SYNTHETICS, S.A.  
Llanos de Jerez, 1  
28820 Coslada (Madrid) Spain  
Tel. (+34) 91 673 69 19  
Fax (+34) 91 674 36 44  
E-mail: [info@texsasynthetics.com](mailto:info@texsasynthetics.com)  
<http://www.texsasynthetics.com>

# Vinitex WS 1.2

Non-reinforced flexible membrane

Dimensions: 2,05 m x 20 m x 1.2 mm

Applications: water-proofing reservoirs, ponds or channels, suitable for outdoor use.

SPECIFICATIONS	Test method	Unit	Vinitex WS 1.2
Tensile Strength at Break	ISO R 527	Mpa N/50 mm	≥ 10 -
Permeability to water	UNE-EN-1928		Pass
Static puncturing	EN ISO 12236	KN	≥ 0.35
Weathering; Changes to stretching and breaking	EN 12224	%	≤ 10

OTHER SPECIFICATIONS	Test method	Unit	Value
Visible defects	EN 1850-2	-	Pass
Length	EN 1848-2	m	20
Width	EN 1848-2	m	2
Straightness	EN 1848-2	mm	≤ 50
Mass per unit area	EN 1849-2	kg/m <sup>2</sup>	1.53
Thickness	EN 1849-2	mm	1.2
Flatness	EN 1848-2	mm	≤ 10
Dimensional stability	EN 1107-2	%	≤ 2
Flexibility at low temperatures	EN 495-5	°C	≤ - 25
Water vapour transmission properties	EN 1931	μ	20.000